

## **ABSTRAK**

Campuran beton geopolimer yang digunakan adalah supeplasticizer 3% untuk semua specimen, benda uji pertama kuat tekan dengan penggunaan 98% semen dengan substitusi Slag 4%  $BSL4_{(1,2,3)}$ , benda uji kedua kuat tarik belah,  $BSL4_{(4,5,6)}$ , benda uji ketiga kuat lentur,  $BSL4_{(7,8)}$ . Benda uji berupa Silinder (Diameter 15cm x 30cm) dan balok (150cm x 150cm x 600 cm), mutu beton yang direncanakan 30 MPa pada umur 28 hari. dengan terlebih dahulu dilakukan perawatan dengan metode perendaman didalam bak air.

Dari hasil pengujian kuat tekan sebagai berikut  $BSL4_{(1)}$  (28,86 Mpa),  $BSL4_{(2)}$  (35,65 Mpa), dan  $BSL4_{(3)}$  (39,61 Mpa). Pengujian kuat tarik belah sebagai berikut  $BSL4_{(4)}$  (3,54 Mpa),  $BSL4_{(5)}$  (3,61 Mpa), dan  $BSL4_{(6)}$  (3,68 Mpa). Pengujian kuat lentur sebagai berikut  $BSL4_{(7)}$  (2,31 Mpa) dan  $BSL4_{(8)}$  (4,06 Mpa). Sedangkan nilai kuat lentur teoritis yaitu 3,902 Mpa, hasil dari kuat lentur aktual tersebut melebihi dari hasil kuat lentur teoritis.

Kata Kunci : Beton Mutu Tinggi, Superplasticizer, Beton Slag, Kuat Tekan, Kuat Tarik Belah,Kuat Lentur.

## **ABSTRACT**

*The geopolymers concrete mixture used is a 3% superplasticizer for all specimens, the first test object is compressive strength using 98% cement with substitution Slag 4% BSL4<sub>(1,2,3)</sub>, the second test object is split tensile strength, BSL4<sub>(4,5,6)</sub>, the third specimen flexural strength, BSL4<sub>(7,8)</sub>. The test object is in the form of a cylinder (diameter 15cm x 30cm) and beam (150cm x 150cm x 600 cm), the quality of the concrete is planned to be 30 MPa at the age of 28 days. by first doing the treatment by soaking in a water bath.*

*From the results of the compressive strength test as follows BSL4<sub>(1)</sub> (28,86 Mpa), BSL4<sub>(2)</sub> (35,65 Mpa), and BSL4<sub>(3)</sub> (39,61 Mpa). Tests for split tensile strength are as follows BSL4<sub>(4)</sub> (3,54 Mpa), BSL4<sub>(5)</sub> (3,61 Mpa), and BSL4<sub>(6)</sub> (3,68 Mpa). Flexural strength testing as follows BSF7<sub>(7)</sub> (2,31 Mpa) and BSL4<sub>(8)</sub> (4.06 Mpa). While the theoretical flexural strength value is 3,902 Mpa, the result of the actual bending strength exceeds the theoretical flexural strength.*

*Keywords : High Quality Concrete, Superplasticizer, Slag Concrete, Compressive Strength, Tensile Strength, Flexibil*

